

# MAINTENANCE INSTRUCTION

## Care Level 4



### BASIC FINISHING after installation:

- » Basic cleaning with WOCA Wood Cleaner & care with WOCA Maintenance Care:
  1. Clean the floor with 125 ml WOCA Wood Cleaner mixed into 5 litres of water. Leave the floor to dry for at least 8 hours.
  2. WOCA Maintenance Care should be shaken well before use and apply carefully (Maintenance Care natural for natural oiled wood floors, Maintenance Care white for white oiled wood floors); apply approx. 100 ml oil per 4 m<sup>2</sup> surface with pad, cotton cloth or Spray, or use polishing machine for large surfaces.
  3. It is important that the Maintenance Oil is carefully polished into the wood. Continue polishing until the wood appears saturated and the surface looks uniform.
  4. Wipe the floor with clean, dry oil suction cloths, or if necessary with the polishing machine before proceeding with the next section of floor to be finished. The floor should not appear wet and there should not be any excess oil left on the surface after polishing. Continue stepwise till the floor has been finished.

When polished with the polishing machine the floor will be pre-hardened after approx. 4 hours at 20°C, manually polished floors after 24 hours. Afterwards the floor may be partly covered with HAFRO Covering Fleece and may be taken into use carefully. Do not expose the floor to water during hardening time and for the first days.

### MAINTENANCE CARE:

- » Daily cleaning with vacuum cleaner or broom
- » Regular cleaning with WOCA Natural Soap:
  1. Shake well the Natural Soap (natural for natural oiled wood floors, white for white oiled wood floors) before use.
  2. 125 ml Natural Soap is mixed with 5 litres of lukewarm water. It is recommended always to work with 2 buckets: one with soap water and one with rinsing water. Clean the floor with minimum quantity of water – leave soap water on floor briefly in order to dissolve dirt. Remove dirty soap water with hard-wrung HAFRO mop or cloth and rinse out in bucket with rinsing water.
  3. Always wipe floor with soap water on hard-wrung mop or cloth in order to re-establish the protective Natural Soap film.or
  - » Cleaning with HAFRO Ready Mixed Wood Floor Soap - for quick cleaning in between:
    1. Prepare HAFRO Mop 3000 with cotton cover, fill the water tank with HAFRO Ready Mixed Wood Floor Soap natural (ready-mixed).
    2. Spray HAFRO Ready Mixed evenly onto the floor (avoid puddles) and wipe.

### REFRESHING:

- » Basic cleaning with WOCA Wood Cleaner & care with WOCA Maintenance Care:
  1. Clean the floor with 125 ml WOCA Wood Cleaner mixed into 5 litres of water. Leave the floor to dry for at least 8 hours.
  2. WOCA Maintenance Care should be shaken well before use and apply carefully (Maintenance Care natural for natural oiled wood floors, Maintenance Care white for white oiled wood floors); apply approx. 100 ml oil per 4 m<sup>2</sup> surface with pad, cotton cloth or Spray, or use polishing machine for large surfaces.
  3. It is important that the Maintenance Oil is carefully polished into the wood. Continue polishing until the wood appears saturated and the surface looks uniform.
  4. Wipe the floor with clean, dry oil suction cloths, or if necessary with the polishing machine before proceeding with the next section of floor to be finished. The floor should not appear wet and there should not be any excess oil left on the surface after polishing. Continue stepwise till the floor has been finished.

When polished with the polishing machine the floor will be pre-hardened after approx. 4 hours at 20°C, manually polished floors after 24 hours. Afterwards the floor may be partly covered with HAFRO Covering Fleece and may be taken into use carefully. Do not expose the floor to water during hardening time and for the first days.

**Warning: Cloths, saturated with oil, may spontaneously combust. After usage, they need to be soaked in water before disposal.**